



Specialty Paints & Products for
Sign · Branding · Re-Imaging
1.800.421.7961

Q-COAT TC™ TRANSPARENT COATING

Q-COAT TC™ is a transparent coating used in the manufacture of plastic backlit signage. **Q-COAT TC™** is a combination of high performance acrylic resins, pigments, special solvents and additives to assure maximum non-mottling spray application and long-term product performance.

Q-COAT TC™ is available in a fast dry binder (Q-BASE PB0001™ or Q-BASE PB0002™) for semi-rigid or rigid substrates with maximum mar resistance or a moldable binder (Q-BASE PB0005™ or Q-BASE PB0007™) for flexible, non rigid substrates when pliability and maximum adhesion is required.

QHF Environmentally Friendly Product.

RECOMMENDED SURFACE APPLICATIONS:

Polycarbonate, acrylic, impact modified acrylic, CAB, ABS, styrene, and most flexible vinyl.
Many existing translucent plastic paint finishes. Test plastic compatibility prior to production runs.

Application of **Q-COAT TC™** on any first surface substrate for exterior application requires a protective sealer **Q-PRIM™ PP1010™** followed by an exterior clear UV topcoat for durability.

APPLICATION:

1.



Safety:

Use only NIOSH approved respirators and personal protection equipment recommended for the product used.

Always review the MSDS – Material Safety Data Sheets before use.

2.



Surface Cleaning:

Remove plastic surface contaminates with **Q-SOLV™ CD4402™** Plastic Cleaner utilizing clean QH&F lint free cloths.


3.



Static Electricity Removal:

Remove static electricity with **Q-SOLV™ CD4402™** Plastic Cleaner utilizing a clean QH&F Chamois.

4.



Reduction Ratio: (Most Common)


1 part **Q-COAT TC™** Plastic Coating Color
1-2 parts **Q-SOLV™** AR Series Reducer(s)



Specialty Paints & Products for
Sign · Branding · Re-Imaging
1.800.421.7961

Q-COAT TC™ TRANSPARENT COATING

5.



Reduction Ratio: (Dark or Difficult to Spray Colors)

1 part **Q-COAT TC™** Plastic Coating Color
1 part **Q-BASE™** PB Series Binder(s)
1 part **Q-SOLV™** AR Series Reducer(s)

6.



Spray Gun Recommendations:

Gravity Feed 1.3-1.4 mm
Siphon Feed 1.6-1.8 mm
Pressure Feed 1.0-1.4 mm

7.



Spray Application:

Apply approximately 4 – 8 coats. More coats may be used to obtain the color translucency required. A back lighted spray booth is recommended to determine when color and translucency is acceptable when compared to the standard color chip. Flash off time between coats should be determined by surface area and ambient temperature.

8.



Dry Time:

Dry to handle at 75°F 50% R.H. in 20-30 minutes. Dry to package and ship in a moisture free environment at 24 hours minimum.

Q-SOLV™ REDUCER SELECTIONS:

AR0055™ Alcohol Fast Reducer

Suitable for temperatures below 70°F.

AR0066™ Alcohol Medium Reducer

Suitable for temperatures between 70°F–85°F.

AR0071™ Alcohol Slow Reducer

Suitable for temperatures above 85°F.

AR0077™ Alcohol Retarder

Recommended only in small quantities of 5-10% by volume in addition to AR Series Reducer when experiencing extremely high temperature and humid conditions.



Specialty Paints & Products for
Sign · Branding · Re-Imaging
1.800.421.7961

Q-COAT TC™ TRANSPARENT COATING

Q-BASE™ PLASTIC BINDER SELECTIONS:

Q-BASE™ FAST DRY PLASTIC BINDERS:

PB0001™ Clear Binder	Complete translucency in colors with maximum mar and scratch resistance.
PB0002™ Lite Defused Binder	More uniform and faster coverage in fewer passes with maximum mar and scratch resistance.

Q-BASE™ MOLDABE PLASTIC BINDERS:

PB0005™ Clear Moldable Binder	Complete translucency in colors with pliability and maximum adhesion.
PB0007™ Lite Defused Moldable Binder	More uniform and faster coverage in fewer passes with pliability and maximum adhesion.

APPLICATION NOTES:

When spray-painting a backlit sign, it is essential that some type of back lighting be utilized. This will allow the sign painter to apply the paint evenly, obtaining the desired reflected and transmitted color. A standard panel is recommended to determine color acceptability.

When painting translucent colors on plastic, you will be required to build up the paint film slowly. Utilize a color panel standard to determine color and translucency acceptability. If one or two heavy coats are used, undesirable light and dark spots, known as mottling, may occur. Usually 4 coats minimum is required. Allow adequate flash off time between coats.

Note: the 4-coat rule is a guideline. The spray pattern, equipment, viscosity, temperature, and operator experience will play an important role in achieving the desired result.

When spraying dark, difficult colors or hard to reach areas it may be necessary to add additional **Q-BASE™** PB Series Binder(s) in a proportion of 1:1 by volume before adding **Q-SOLV™** AR Series Reducer(s). This will allow you to apply more coats evenly. This technique can be used with any color to obtain a more even film build.

Always test surface preparation, primer and topcoat compatibility to determine acceptability before any production run.

Disclaimer: Technical information and suggested uses are believed to be reliable by QH&F Ltd., but such information or suggestions do not constitute a warranty. QH&F Ltd. has no control over the conditions under which the product is stored, handled, used or applied. Buyers must determine for themselves the suitability of each product for their specific use.

® is a registered trademark and ™ is a trademark of Quill Hair & Ferrule LTD. Copyright © 2009. Quill Hair and Ferrule LTD. All Rights Reserved.